

Vat Dyes Powder for Textiles

Apavat®PT

Color Shade	Apavat®PT	C.I.No (Vat)	Dyeing Depth o.w.f %	Fastness							Dyeing Method
				Light (xenon)	Washing (95°C)		Perspiration		Rubbing		
					CH	CO	CH	CO	Dry	Wet	
	Yellow G 100%	Yellow 1	4.0	6-7	5	5	5	5	5	4-5	1N
	Yellow GCN 100%	Yellow 2	4.0	4	4-5	4-5	4-5	4-5	4-5	4	1N
	Yellow F3GC 100%	Yellow 33	4.0	6-7	5	4-5	5	4-5	4-5	4	1W
	Yellow 5GF 100%	Yellow 46	4.0	6	4-5	5	5	4-5	4-5	4	1N
	Yellow 3GL 100%	Yellow 48	4.0	6-7	5	5	5	5	5	5	1N
	Golden Yellow RK 100%	Orange 1	4.0	6-7	4-5	4	4-5	4-5	4	3	1W
	Golden Orange 2RT 100%	Orange 2	4.0	5-6	4-5	5	5	5	4-5	4	1W
	Brill. Orange 3RK 100%	Orange 3	4.0	7	4-5	5	5	5	3-4	3	SRI
	Brill. Orange GR 100%	Orange 7	4.0	6	5	5	4-5	5	4-5	3-4	1N
	Golden Orange G 100%	Orange 9	4.0	5-6	4-5	4-5	4	4-5	4-5	4	1N
	Yellow 3RT 100%	Orange 11	4.0	7	5	5	4	4	4-5	4	1N
	Orange 3G 100%	Orange 15	4.0	6	5	5	4	4	4-5	4	1N
	Pink R 100%	Red 1	4.0	6	4-5	5	4-5	4-5	4-5	4	SRII
	Brill. Red 3B 100%	Red 3	4.0	6	4-5	5	4-5	4	4-5	4	1N
	Red FFB 100%	Red 10	4.0	6-7	4	4	4-5	5	2-3	4	1W
	Rubine 6B 100%	Red 13	4.0	7-8	4	4	4	3-4	3-4	2-3	1N
	Scarlet GG 100%	Red 14	4.0	7	4-5	5	4	4-5	4-5	3-4	1N
	Bordeaux RR 100%	Red 15	4.0	6-7	4-5	4-5	4	5	4-5	3-4	1N
	Scarlet R 100%	Red 29	4.0	6	4-5	5	4-5	5	3-4	2-3	1W
	Red F3B 100%	Red 31	4.0	6-7	5	5	4	4-5	4-5	3	1W
	Red BB 100%	Red 32	4.0	5	3-4	4-5	4-5	4	4	4	1W
	Red EFR 100%	Red 54	4.0	6	2-3	3-4	3-4	4-5	4-5	3	1N
	Brown BR 100%	Brown 1	4.0	7	4-5	4-5	4-5	5	4-5	4	1W
	Brown R 100%	Brown 3	4.0	7-8	5	5	4	4-5	4-5	4-5	1N
	Brown LG 100%	Brown 23	4.0	5-6	4-5	2	3-4	4	3-4	2	1N
	Brown 2R 100%	Brown 57	4.0	7-8	5	4	5	4	4	3-4	1N

Vat Dyes Powder for Textiles

Apavat®PT

Color Shade	Apavat®PT	C.I.No (Vat)	Dyeing Depth o.w.f %	Fastness							Dyeing Method
				Light (xenon)	Washing (95°C)		Perspiration		Rubbing		
					CH	CO	CH	CO	Dry	Wet	
	Brown G 100%	Brown 68	4.0	7-8	4-5	5	4-5	5	4-5	4	1W
	Brown GG 100%	Brown 72	4.0	7-8	5	5	5	5	4-5	4-5	1W
	Brown LBG	Brown 84	4.0	6-7	5	5	5	5	4-5	4-5	1W
	Indigo Blue 94%	Blue 1	4.0	3-4	2	4	2-3	2-3	1-2	1	SRI
	Blue RSN 100%	Blue 4	4.0	7-8	4-5	4-5	4-5	4-5	4	3-4	1N
	Blue BC 100%	Blue 6	4.0	7-8	4-5	5	4-5	5	4-5	4-5	1N
	Blue RCL 100%	Blue 6:1 Mix	4.0	7-8	4-5	5	4-5	5	4-5	4-5	1N
	Blue GCDN 100%	Blue 14	4.0	7-8	5	5	4-5	5	4-5	4	1N
	Dark Blue G 100%	Blue 16	4.0	7-8	5	5	4-5	5	4-5	4	1N
	Navy RAN 100%	Blue 18	4.0	7	3-4	4-5	4	4	4	3	1N
	Blue Bo 100%	Blue 20	4.0	7-8	3-4	4-5	4-5	4-5	4	3	1N
	Blue SR 100%	Blue 22	4.0	6-7	3-4	4-5	4-5	4-5	4	3	1N
	Sulphur Vat Blue GNX100%	Blue 42	4.0	5	4-5	3-4	4-5	4-5	3-4	2-3	1N
	Sulphur Vat Blue RNX100%	Blue 43	4.0	6-7	4	4-5	4-5	4-5	3	1-2	1N
	Blue CLF 100%	Blue 66	4.0	6	4	4-5	4-5	4-5	3	1-2	1N
	Navy Blue R 100%	Blue mix	3.0	7	4-5	4-5	4-5	4-5	4-5	4	1N
	Dark Blue VB 100%	Blue mix	3.5	7	4-5	4-5	4-5	4-5	4-5	4	1N
	Black CLG 100%	Black 6	8.0	7-8	4	4-5	4-5	4-5	3	1-2	1N
	Grey M 100%	Black 8	4.0	7	3-4	4-5	4-5	5	4-5	3	1N
	Black RB 100%	Black 9	8.0	7-8	4-5	4-5	3-4	4-5	3-4	2	SRII
	Grey 3B 100%	Black 16	8.0	6-7	4	4-5	4	4	4	3-4	1N
	Olive T 100%	Black 25	4.0	7-8	4-5	4-5	4-5	4-5	4-5	3-4	1N
	Olive R 100%	Black 27	4.0	7	4-5	5	4-5	4-5	4-5	4	1W
	Grey BG 100%	Black 29	6.0	6-7	4-5	4-5	4	5	4	3	1W
	Black AC 100%	Black 34	-	-	-	-	-	-	-	-	-
	Black B 100%	Black 38	8.0	6-7	3-4	4	3	4-5	3-4	2-3	1N

Vat Dyes Powder for Textiles

Apavat®PT

Color Shade	Apavat®PT	C.I.No (Vat)	Dyeing Depth o.w.f %	Fastness							Dyeing Method
				Light (xenon)	Washing (95°C)		Perspiration		Rubbing		
					CH	CO	CH	CO	Dry	Wet	
	Black DBMD 100%	Black Mix	-	-	-	-	-	-	-	-	-
	Green FFB 100%	Green 1	4.0	7-8	4-5	5	5	5	4-5	4	1N
	Olive Green B 100%	Green 3	4.0	7-8	4-5	4-5	4-5	4-5	4-5	3	1N
	Green G 100%	Green 7	4.0	6-7	4-5	5	-	-	-	-	1W
	Khaki 2G 100%	Green 8	4.0	7-8	5	5	4	5	4	2	1N
	Black BB 100%	Green 9	4.0	8	4-5	4-5	5	5	4-5	3	1N
	Olive MW 100%	Green 13	4.0	7-8	4-5	4-5	5	5	4-5	4	1N
	Grass Green GN 100%	Green mix	3.0	7	5	5	4	4	4-5	4	1N
	Violet 2R 100%	Violet 1	4.0	6	4-5	4-5	4-5	5	4-5	4	1N
	Violet 3B GN 100%	Violet 9	4.0	5-6	4-5	5	4-5	5	4-5	4	1N
	Violet XBN 100%	Violet 13	4.0	6-7	4-5	5	4-5	5	4-5	4	1N