

Pigment Powder for Textiles

Apament®Textile

Full Colour	Apament®Textile	C.I NO. (Pigment)	Physical Properties				Resistance to Chemicals		Resistance to Solvents					Light Fastness	
			Specific gravity	Bulk volume (lit/kg)	Oil Absorption (gm/100gm)	PH of Aqueous extract	Acid(5%HCL)	5% alkali (NaoH)	water	Ethanol	Xylene	M.E.X	D.O.P	Full shade	Tint shade
	Yellow G	Yellow 1	1.4	4.5	50	7	5	5	5	3	3	3	5	7	6
	Yellow 10G	Yellow 3	1.5	4	50	7	5	5	5	3-4	2	2	2-3	7	7
	Yellow GTP	Yellow 12	1.4	7	42	7	5	5	5	3 -4	4-5	4	4	5-6	5-6
	Fast Yellow GRX	Yellow 13	1.3	5	55	7	5	5	5	4	4	4	4	7	5
	Yellow GRT	Yellow 14	1.6	4	40	7	5	5	5	4 -5	3-4	4	5	7	5
	Yellow GG	Yellow 17	1.3	5	60	7	5	5	5	4 -5	4-5	4	4-5	7	6-7
	Yellow WSR	Yellow 62	1.6	4.3	40	7	5	5	5	4	3	3	3 -4	7	6
	Fast Yellow RN	Yellow 65	1.2	4.1	50	7	5	5	5	4	3-4	2-3	3-4	6-7	7
	Yellow 5GSC	Yellow 74	1.4	3.5	38	7.3	5	5	5	4	2 -3	3-4	3-4	7-8	7-8
	Yellow HR	Yellow 83	1.6	5	60	7	5	5	5	5	5	5	5	8	7
	Fast Yellow H3G	Yellow 154	1.6	4.5	40	7	5	5	4	4-5	4	4	4	8	8
	Red F2R	Red 2	1.5	6	42	7	5	5	5	2	1-2	1-2	3-4	6-7	4-5
	Fast Red R	Red 4	1.45	6	35	7	2 -3	3-4	4-5	2-3	2-3	2-3	3-4	7	6
	Red F4R	Red 8	1.36	5	45	7	5	3	-	3	3	3	2 -3	6-7	6
	Red Toner 2B	Red 48:1	1.5	5	45	7	4	4	5	3-4	4	3-4	3	6-7	6
	Fast Red 2BP	Red 48:2	1.4	5.5	50	7	2-3	4-5	4-5	3-4	4-5	4-5	5	6-7	5
	Fast Red 2BS	Red 48:3	1.4	5.5	50	7	5	5	5	4	4-5	4	3	7	6
	Red SC	Red 49:1	1.4	4	45	7	2 -3	2-3	4-5	3	2-3	2	3	6	5-6
	Red CT	Red 53:1	1.4	6	50	7.1	4	4 -5	5	3-4	3-4	3-4	4	4	3
	Rubine Red SC	Red 57:1	1.4	6	60	7	2 -3	4	4	4	4	3-4	4	5-6	4-5
	Red FGR	Red 112	1.5	7	45	7	5	2	5	3-4	3-4	3-4	3-4	6-7	5-6
	Fast Red SC	Red 122	1.4	3	67	7	5	5	5	5	5	4 -5	5	8	7
	Red FBB	Red 146	1.4	7	55	7	5	5	5	4 -5	4	4	5	6-7	5
	Red F3RK	Red 170	1.36	7	50	7	5	5	5	4-5	5	4-5	5	6-7	6-7
	Permanent Rubine F6G	Red 184	1.6	4 -5	40	6.8	5	5	5	4-5	4	3-4	5	5-6	5
	Fast Orange RN	Orange 5	1.3	5.5	55	7	5	5	5	3-4	3-4	5	4	6-7	5-6

