

Reactive Dyes Powder for Textiles

Apactive® FN

Apactive®FN				Solubility	Light Fastness ISO 150 BO2		Washing Fastness ISO 105 CO4		Perspiration Fastness ISO 105 E04				Chlorinated ISO 105-E03	Rubbing Fastness ISO 105-X12	
Color Shade	OWF		Dye Name		g/l	1/6 SD	1/1 SD	CS	CO	Acid		Alkaline			
										CS	CO	CS			CO
	●	1.2%	Yellow FN - 2R	100	5	5-6	5	5	4-5	5	4-5	5	4	5 4	
	●	1.6%	Red FN - 2BL	60	5-6	5-6	5	5	5	5	5	4.5	2-3	5 3-4	
		2.4%	Brown FNR	100	5-6	5-6	5	5	5	5	5	5	3-4	5 3-4	
	●	2.8%	Blue FNR	100	6	7	5	4-5	4-5	5	4-5	5	3-4	5 4	
		2.4%	Blue FNG	100	4	6-7	5	5	5	5	5	5	1	5 3-4	
		3.0%	Navy FNBR	80	4-5	5	5	5	5	5	5	5	3-4	4-5 3	
	★	0.8%	Grey FNB	100	5-6	5-6	5	5	5	5	5	5	3-4	5 3-4	

●	Tri- Chromatic Combination for medium to deep shade
★	used with olive/khaki/grey shade