

Basic Dyes Powder For Textiles, Papers and Inks

Apasic®PTPI

Color Shade	Apasic®PTPI	C.I. No. (Basic)	Cas No.	Color Index No.	EINES No.	Solubility,g /l	Light Fastness @ 1% owf	IIA wash Test		Crocking		Sublimation a (325 deg F- 30 Sec)	Acid Perspiration
								Shade Change	Staining	Wet	Dry		
	Auramine AU	Yellow 2	2465-27 -2	41000	219-567 -2	75	5-6	5	4-5	4-5	4-5	4	4
	Golden Yellow GL	Yellow 28	54060 -92 -3	48054	258-946 -7	75	6-7	5	5	5	5	5	5
	Chrysoidine R	Orange 1	5042-54 -6	11320	225-736 -1	45	3-4	4-5	4-5	4-5	4-5	4	4
	Chrysoidine G	Orange 2	532-82-1	41000	208-545 -8	40	1-2	5	5	4-5	5	4	4
	Brill. Red 4G	Red 14	12217 -48-0	48016	235-399 -2	80	3-4	4-5	5	5	5	5	5
	Brown G	Brown 1	10114-58 -6	21000	233-314 -3	90	3-4	4-5	4-5	4-5	4-5	4	5
	Brown R	Brown 4	5421-66 -9	21010	226-541 -4	90	3-4	4-5	4-5	4-5	4-5	4	4
	Methylene Blue BB	Blue 9	61-73-4	52015	200-515 -2	70	6-7	4-5	4-5	4-5	4-5	4	4
	Blue B	Blue 26	2580-56 -5	44040	219-943 -6	70	6-7	4-5	4-5	4-5	4-5	4	4
	Blue GRL	Blue 41	12270-13 -2	11105	235-546 -0	80	6-7	5	5	5	5	5	5
	Briilliant Green XLS	Green 1	633-03 -3	42040	211-190 -1	80	3-4	5	4-5	4-5	4-5	4	4
	Malachite Green XLS	Green 4	569-64 -2	42000	209-322 -8	80	2-3	4-5	4-5	4-5	4-5	4-5	4 -5
	Methyl Violet 2B	Violet 1	8004-87 -3	42535	210-042 -3	40	2-3	3	3	4-5	4-5	4	4-2
	Crystal Violet	Violet 3	548-62 -9	42555	208-953 -6	60	3-4	4-5	4-5	4-5	4-5	4	2-3
	Rhodamine B	Violet 10	81-88-9	45170	201-383 -9	60	3-4	4-5	4-5	4-5	4-5	4	3-4
	Rhodamine 3B	Violet 11	2390-63-8	45175	219-233-6	100	3-4	4-5	4-5	4-5	4-5	4	3-4
	Red NV	Violet 11:1	73398-89-7	45174	277-459-0	80	3-4	4-5	4-5	4-5	4-5	4	3-4
	Magenta B	Violet 14	632-99 -5	42510	211-189 -6	60	3-4	4-5	4-5	4-5	4-5	4	3-4
	Violet 3R	Violet 16	6359-45 -1	48013	228-799 -3	90	3-4	4	5	4-5	5	3	4-5